

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 December 2001 (20.12.2001)

PCT

(10) International Publication Number
WO 01/96115 A1

(51) International Patent Classification⁷: B32B 27/36, 17/10, C03C 17/32

(21) International Application Number: PCT/US01/13609

(22) International Filing Date: 27 April 2001 (27.04.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/591,584 9 June 2000 (09.06.2000) US

(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventor: DIETZ, Peter, T.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: KNECHT, Harold, C., III et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: GLAZING ELEMENT AND LAMINATE FOR USE IN THE SAME



(57) Abstract: A multi-layer optically clear laminate suited for attachment to window glass to provide a glazing element which has reduced spill and lacerative consequences on fracture impact of the window glass is provided by the invention. The laminate is comprised of at least two films of nonadhesive polymeric material directly adhered together by pressure sensitive adhesive and includes an exposed surface covered with a hard coat composition and an opposite surface covered with an ambient temperature attachable pressure sensitive adhesive. A glazing element comprised of the laminate attached to glass is also provided.

WO 01/96115 A1

GLAZING ELEMENT AND LAMINATE FOR USE IN THE SAME

5

Background of the Invention

Field of the Invention

10 This invention relates to a multi-layer optically clear laminate suited for attachment to window glass to provide a glazing element which has reduced spall and lacerative consequences on impact fracture of the window glass and to glazing elements made with the same.

Description of Related Art

15 The invention of laminated glass windshields for use in motor vehicles has substantially reduced injuries caused by occupant-windshield impacts resulting from automobile accidents. Such laminated windshields are made by laminating under heat and pressure two glass plates with an interlayer of a tough, transparent, extensible, material such as polyvinyl butyral (PVB). While such a laminated windshield provides some degree of protection for motor vehicle occupants, it is still generally conventional to utilize
20 unlaminated glazing elements for fabricating the other windows of automobiles. While such windows are typically tempered so that on impact they fracture in small irregular pieces without producing knife-like shards, they still provide a hazard to the occupants of a motor vehicle. The impact fracture of such automotive glazing typically produces what is called "spall." Spall is the shower of glass splinters that typically results from the
25 impact fracturing of automotive glazing. Such glass splinters could have a lacerative effect on the occupants of the motor vehicle and on any air bag that may have been inflated as a result of the automobile accident.

There is a growing trend to replace tempered glass with laminated glass (glass/PVB/glass) as motor vehicle sidelights to provide additional safety. However, when
30 laminated sidelights are broken, they typically leave sharp glass shards attached to the PVB interlayer which can cause severe laceration to the occupants of the vehicle. Thus, a need exists for an acceptable anti-spall, anti-lacerative (ASL) film that will provide a

barrier between the broken glass shards and the vehicle occupant to minimize the opportunity for laceration.

Furthermore, in the case of automobiles, there is a practice called "smash and grab" utilized by thieves intending to steal the contents of automobiles which provides
5 immediate access on impact of tempered glass automotive windows. A need also exists for a stronger window film which will sustain such fractures without rupture.

The impact fracture problem also exists in the case of architectural glazing where tempered or annealed glass panels are employed for windows and doorways. Impact
10 fracturing of such glass panels may cause spall which would be a hazard to anyone in the immediate vicinity of the fractured panel.

The use of laminates to reinforce glazing is well known. For example, U.S. Patent No. 4,072,779 (Knox, et al.) is directed to a laminate which includes a frangible, transparent, asymmetrically oriented polyethylene terephthalate film laminated to a
15 polyvinyl butyral sheet and coated on the opposite surface with an abrasion-resistant coating. This laminate is adhered to a glass panel by sandwiching it between the glass panel and a second glass panel under heat and pressure and discarding the nonadhered glass panel once the lamination is completed. It is believed that the laminate is commercially available from the E. I. DuPont de Nemours and Company, Circleville, Ohio under one or more of the tradenames SENTRY GLASS™ and BE-1028
20 SPALLSHIELD™ sheeting.

U.S. Patent No. 4,112,171 (Mottet, et al.) discloses a laminate which is said to provide anti-lacerative and anti-spall properties. U.S. Patent No. 4,945,002 (Tanuma, et al.) discloses an impact-resisting anti-lacerative window glass unit comprised of two
25 exterior plate-like members made of a transparent organic first polymer and a transparent organic second polymer or glass plate to provide a multilayered structure wherein the intermediate layer could be polyethylene terephthalate.

U.S. Patent No. 4,683,172 (LeGrand, et al.) discloses a safety or impact resistant laminate comprised of at least two laminae with an interlayer imposed therebetween
bonded together by contact or pressure sensitive adhesive. The interlayer is said to be
30 what is known in the art as an adhesive interlayer such as polyvinyl butyral.

While there is a multitude of patents disclosing various combinations of providing anti-spall and anti-lacerative laminates, none has produced a commercially acceptable

product which is easy to apply under ambient conditions to provide a commercially acceptable result. Many of the products are relatively thick and thus difficult to apply, requiring heat, pressure and/or expensive application equipment. Others may not withstand the rigors of changing seasons where during winter an automotive interior may be cooled to frigid temperatures and in the summer may be heated to a sweltering temperature. Others have inherent problems because of incompatibility of some of the materials forming the laminate. Some materials will cause undesirable optical patterns when attached to automotive glazing material. Still others are frangible and do not provide the necessary strength to sustain a fracture producing impact of the glass panel while still providing the anti-spall and anti-lacerative effect.

Summary of the Invention

The invention provides an optically clear laminate suited for attachment to tempered or laminated window glass to provide a glazing element which has reduced spall and lacerative consequences on impact fracture of the window glass. The laminate is easily installed under ambient conditions with an inexpensive roller and, once installed, provides superior anti-spall and anti-lacerative properties and sufficient strength, even after impact fracture, to deter smash and grab thieves. The laminate comprises:

- (a) a first lamina comprised of optically clear flexible nonadhesive polymeric material having a first major surface and an opposite second major surface;
- (b) a scratch-resistant hard coating over said first major surface to provide an exposed surface to the laminate;
- (c) at least one additional lamina comprised of optically clear flexible nonadhesive polymeric material;
- (d) a sufficient number of layers of in situ optically clear pressure sensitive adhesive layers to directly bond said laminae together with the hard coating exposed; and
- (e) a layer of in situ optically clear, ambient-temperature-attachable, pressure sensitive adhesive to bond said laminate to window glass.

The preferred laminates of the invention include pressure sensitive adhesive compositions having a shear storage modulus in the range of about 0.20 to 0.50 MPa when measured at 22°C. The preferred shear storage modulus is about 0.3 MPa.

The invention further provides an optically clear glazing element which has reduced spall and lacerative consequences on impact fracture. The glazing element comprises the optically clear laminate of the invention adhered to tempered or laminated window glass.

5 The preferred optically clear laminate of the invention comprises the following components which are adhered together in the order shown below:

- (a) a first biaxially oriented polyester film having a thickness of not more than about 5 mils (0.13 mm);
- (b) a first pressure sensitive adhesive layer;
- 10 (c) a second biaxially oriented polyester film having a thickness of not more than about 5 mils (0.13 mm);
- (d) a second pressure sensitive adhesive layer;
- (e) a third biaxially oriented polyester film having a thickness of not more than about 5 mils (0.13 mm); and
- 15 (f) a third ambient-temperature-attachable pressure sensitive adhesive layer.

The laminates according to the invention are preferably relatively thin in overall thickness to facilitate easy mounting under ambient conditions on flat or curved glass surfaces by application of pressure by use of a simple roller. Preferably the total laminate thickness does not exceed about 20 mils (0.5 mm), more preferably does not exceed about 20 15 mils (0.38 mm) and most preferably does not exceed about 12 mils (0.3 mm). Suitable laminates may have a thickness in the range of about 8 to 10 mils (0.2 to 0.25 mm). The total laminate thickness is the combined thickness of all of its components except that of the release liner. The lower useful practical thickness is that at which the laminate becomes too flimsy to be readily handled, no longer has the desired physical properties or 25 is too difficult to process. The total thickness preferably exceeds about 5 mils (0.13 mm).

The laminates of the invention have lamina comprised nonadhesive polymeric material that are "directly" adhered together by pressure sensitive adhesive, with no adhesive interlayers other than the layer of pressure sensitive adhesive, to provide a tough laminated structure which will easily retain impact fractures.

30

Brief Description of the Drawings

For a better understanding of the invention, reference is made to the attached drawing, wherein:

Fig 1 is an enlarged sectional view of an optically clear glazing element of the invention;

Fig. 2 is an enlarged sectional view of an optically clear laminate of the invention; and

Figs. 3 and 4 are schematic diagrams showing details of the preparation of the laminate of the invention.

Detailed Description

Referring to Fig. 1 of the drawing, a laminate 11 according to the invention comprises hard coat 12 adhered to plastic film 13 which is laminated to plastic film 15 by pressure sensitive adhesive layer 14 and includes on the opposite side of plastic film 15 a layer of ambient-temperature-attachable pressure sensitive adhesive 16 for mounting laminate 11 to the attachment surface of a sheet of glass 17. Glazing element 10 is provided when laminate 11 is adhered to a sheet of glass 17. By "ambient-temperature-attachable" is meant that the pressure sensitive adhesive may be adhered to the surface of glass without requiring external heating of the elements, although in some cases, moderate heating may be employed to provide better conformability.

A preferred laminate 20 according to the invention is shown in Fig. 2 of the drawing. It includes hard coat layer 21 adhered to first plastic film 22 which is laminated to second plastic film 24 by pressure sensitive adhesive layer 23. Second plastic film 24, in turn, is laminated to third plastic film 26 by pressure sensitive adhesive layer 25. An additional ambient-temperature-attachable pressure sensitive adhesive layer 27 is on the opposite side of plastic film 26 for mounting the laminate to the surface of a glass window. For convenience in storing the laminate it is preferred to have a release liner 28 to protect the exposed surface of mounting adhesive layer 27.

The hard coat 12 or 21 may be obtained by applying any commercially available hard coating composition to the surface of plastic film 13 or 22, as the case may be, provided that the resultant hard coated layer dries to form a scratch-resistant surface which will pass the abrasion for plastics test established by the American National Standard for

Safety Glazing Materials for Glazing Motor Vehicles and Motor Vehicle Equipment Operating on Land Highways safety code (ANSI/SAE Z26.1-1996) approved by the American National Standards Institute August 11, 1997, incorporated herein by reference.

5 A preferred hard coating composition is a ceramer coating composition comprising an organic resin and silica particles as described in assignee's U.S. Patent No. 5,677,050, incorporated herein by reference. This coating composition may comprise about 20% to about 80% of ethylenically unsaturated monomers; about 10% to about 50% of acrylate functionalized colloidal silica; and about 5% to about 40% of N,N-disubstituted acrylamide monomer or N-substituted-N-vinyl-amide monomer; wherein the percentages
10 are by weight of the total weight of the coating. The coating is then cured to provide an abrasion-resistant, light transmissive ceramer coating on the top film lamina of the laminate. The hard coating is preferably applied to the film before it is used to form the laminate.

The amide monomer should be a N,N-disubstituted monomer or a N-substituted-N-vinyl-amide monomer. It has been discovered that use of an acrylic acid or acrylic ester
15 in place of the N,N-disubstituted acrylamide or N-substituted-N-vinyl-amide monomer yields coatings that adhere poorly to polycarbonate surfaces and do not weather well. The use of acrylated urethanes in place of the N,N-disubstituted acrylamide or N-substituted-N-vinyl-amide monomer results in intractable compositions.

20 The N,N-disubstituted acrylamide or N-substituted-N-vinyl-amide monomer should also have a molecular weight between 99 (the molecular weight of N,N-dimethylacrylamide) and 500 atomic mass units. This molecular weight range is desired for stabilizing the silica particles and for proper functioning of the coating.

In the present invention, the term "ceramer" is used to identify a fluid comprising
25 surface-modified colloidal silica particles dispersed in a free-radically polymerizable organic liquid. The term "cured ceramer" is used to identify a material comprising inorganic (specifically, silica) particles attached or connected via covalent linkages to a crosslinked organic matrix. The term "acrylate," as used herein, encompasses acrylates and methacrylates. The term "disubstituted nitrogen" means that the acrylamide nitrogen
30 atom, in addition to being the nitrogen of the acrylamide, has two substituents covalently bonded to the nitrogen. The term "optically clear," means that the laminate or any of its components, e.g., hard coating, film or pressure sensitive adhesive layer in situ exhibit a

light transmittance, as measured by ASTM D1003, of at least 75%, preferably at least 85% and more preferably at least 90%.

The ceramer composition or other hard coating compositions can be coated on the film by methods known in the art, including: extrusion coating, spraying, flowing, rolling, dip coating or knife coating. In many applications it is desirable to coat the film without allowing the coating composition to flow onto the backside of the film because this may diminish its optical characteristics. After the composition is coated onto the film, it is cured to form the abrasion-resistant ceramer coating. Since the film has a front surface made from a thermoplastic material, it is important in many instances that curing is conducted at a temperature below that at which the thermoplastic material deforms, and is preferably irradiated by UV light at room temperature in an air atmosphere.

The ceramer coating provides both excellent abrasion resistance and good flexibility. Coatings also adhere to polymer films especially polycarbonate films, without fogging, hazing or the addition of priming agents.

The ceramer coating also has the ability to withstand outdoor conditions with excellent resistance to moisture, light and heat; resistance to cracking and peeling; desirable optical properties such as transparency; and resistance to chemical attack and unwanted coloration.

Moreover, the coatings can be easily formulated, applied and cured, and they can be used without a primer layer because of their ability to bond directly to the surface of the polymer film. Curing of the coatings may be conducted in air at room temperature.

The coating thickness of the hard coating may vary from about 0.1 mil (0.003 mm) to about 0.3 mil (0.008 mm), but preferably is on the order of 0.004 mm to provide an add on weight to the coated sheet of about 1.5 gram per square meter to 3.8 grams per square meter.

Polymeric film 13, 14, 22, 24 and 26 may be comprised of any polymeric material which is nonadhesive that may be formed into a sheet which is of substantially uniform thickness along its entire area and is optically clear with substantially no surface imperfections which might interfere with optical clarity. The term "nonadhesive" means that the polymeric material used to form the film is not an adhesive type material such as conventionally used to make glass or layered film laminates. Such adhesive polymeric materials would include thermoplastic adhesive materials such as polyvinyl butyral,

ethylene terpolymers, epoxies, polyurethanes, silicones and acrylic polymers. The polymeric films may vary in thickness from about 0.5 mil to about 10 mils (0.013 to 0.25 mm), but preferably do not exceed about 5 mils (0.13 mm) in thickness. The films may be made of polymeric material such as polyethylene-terephthalate which when formed into a sheet, biaxially oriented and heat set provides a high breaking strength film with excellent optical properties. Certain useful polymeric films such as polycarbonate and polyurethane films are typically cast and thus not biaxially oriented to improve strength. Preferably, the polymeric films are primed or corona treated to improve adhesion between coatings and adhesive layers.

In an alternative embodiment, one of the layers of polymeric film may be replaced with an infrared reflecting optical film. Such films include dielectric multi-layer optical films disclosed in assignee's U.S. Patent Nos. 5,882,774 and 6,049,419 and WO97/01778, each of which is incorporated herein by reference. Such films, which are polymeric having no additional metal layer, are particularly useful for being laminated to curved glass panels.

A useful conformable infrared reflecting film which may be applied to non-planar glass substrates to provide a wrinkle-resistant laminate is disclosed in assignee's U.S. Patent Serial No. 09/590,924, entitled Wrinkle-Resistant Infrared Reflecting Film and Non-Planar Laminate Articles Made Therewith.

A preferred primed polymeric film is commercially available from the E. I. DuPont de Nemours and Company under the trade designation MELINEX™ polyester film type 454-200. The preferred film has a thickness of about 50 μm (200 gauge) and has an elongation at break of about 150 percent and a tensile strength of about 20 kgf/mm^2 in the machine direction and 25 kgf/mm^2 in the transverse direction.

The polymeric film or coating may be modified to provide other desired properties to the laminate. For example, one or more of the laminae or coating may be treated with or composed of a material which can reflect infrared light, ultraviolet light, sunlight or other forms of unwanted radiant energy. As an example, the solar reflecting film may be that available under the trade designations XIR™ -70 and XIR™ -75 from Southwall Technologies, Inc. of Palo Alto, CA. The film or coating may also be treated with or composed of materials which would prevent viewing therethrough to provide privacy to the vehicle occupants. As an example, a film which acts as a light polarizer may be

employed as one of the films of the laminate. The films or the coating may also be colored by the addition of suitable colorants. The coating may also be provided with an antifogging agent to prevent its surface from fogging under certain conditions or a material that provides a surface which resists smudging. The coating and/or one or more of the
5 films may be modified to be electrically conductive to provide an electrically conductive path for certain applications such as to provide an antenna or a heating element to eliminate or reduce fogging, mist or frost. The laminate or one or more of its components may also be embossed or treated to provide a holographic pattern for decorative or functional reasons. The modifications, additives or compositions which provide these
10 properties are well known and they may be provided over the full expanse of the laminate or over portions of the laminate, in functional or decorative patterns.

The pressure sensitive adhesive layers between plastic films, i.e., adhesive layers 14, 23 and 25 may comprise any relatively soft pressure sensitive adhesive material that is in situ optically clear. That is, the pressure sensitive adhesive material may, itself, not be
15 optically clear in a free standing condition but once incorporated into the laminate will have an optically clear condition and sufficient adhesion to maintain the layers of the laminate in an unaltered form over any of a wide variety of climatic conditions including severe freezing conditions and sweltering heat as may be encountered in areas near the Equator. The adhesive should also be sufficient to maintain the laminate unaltered
20 through any boiling water test according to the standards of ANSI/SAE.

Preferred pressure sensitive adhesive compositions are relatively soft materials which provide a conformable laminate. Such soft pressure sensitive adhesive compositions are characterized by having a shear storage modulus as measured by Dynamic Mechanical Analysis (DMA) at 22°C in the range of about 0.20 to about 0.50
25 MPa; preferably, the shear storage modulus at 22°C is no greater than 0.50 MPa, more preferably, no greater than 0.40 MPa, and most preferably about 0.30 MPa. Pressure sensitive adhesives having a shear storage modulus of 0.20 MPa or lower are generally not preferred because they generally have insufficient adhesion especially under warm conditions. The shear storage modulus may be calculated from the shear stress measured
30 in the temperature range of -20°C to 100°C using an amplitude of 15 micron, and a frequency of 1 hertz. More details about this measurement may be found in ASTM D-

4065-95, Standard Practice for Determining and Reporting Dynamic Mechanical Properties of Plastics.

Preferred pressure sensitive adhesive compositions are based on acrylate or acrylic copolymers and terpolymers with the most preferred adhesive composition being those disclosed in assignee's Ulrich U.S. Reissue Patent No. 24,906.

The thickness of the pressure sensitive adhesive layers utilized to adhere the polymeric film layers may vary from about 0.1 mil to about 1 mil (0.003 to 0.03 mm), but preferably is on the order of 0.3 mil (0.02 mm).

The layer of pressure sensitive adhesive intended to mount the laminate to the surface of a glass sheet, e.g., layers 17 and 27, will have the same physical properties as the pressure sensitive adhesive utilized to adhere together the polymeric film layers, but the thickness of the mounting layers may vary from about 0.1 mil to about 2 mils (0.003 to 0.05 mm), but preferably is on the order of 0.8 mil (0.02 mm).

The glass to which the laminate may be attached may have any conventional structure or composition. For example, the glass may be laminated, as in conventional windshield glass, tempered, annealed, heat strengthened or, in fact, may be a rigid sheet of hard polymeric material such as a sheet of polymethylmethacrylate resin such as that sold under the trade designation LUCITE™. Preferred glass substrates are either tempered or laminated.

Release liner 28 may comprise any conventional sheet material which has temporary weak adhesion for the pressure sensitive adhesive surface to which it is applied and will strip cleanly from that surface to leave an unaltered layer of pressure sensitive adhesive for attachment to the surface of a glass sheet.

The laminate 11 depicted in Fig. 1 may conveniently be prepared by utilizing equipment schematically shown in Figs. 3 and 4. As shown in Fig. 3, a roll 30 of polymeric film such as that available under the trade designation MELINEX™ 454-200 film is obtained from a commercial source. Plastic film 31 is drawn from roll 30, passed over roll 33b and 33a which deploys film 31 to receive a coating of the hard coat material from coater 32 to provide a wet coating of coating material which will dry to an add on weight on the order of 0.1 to 0.5 gram per square foot (0.8 to 3.8 grams per square meter), preferably 0.3 gram per square foot (3.2 grams per square meter). Coater 32 may be any convenient coating device such as one including a slot die to provide a uniform coating to

the surface of film 31. The slot die may have an opening on the order of 2 to 6 mils (0.05 to 0.15 mm), but preferably the opening is on the order of 4 mils (0.1 mm) to obtain the preferred 0.3 gram per square foot (3.2 grams per square meter) add on weight. The coating solution may be any commercially available hard coating solution which has the appropriate viscosity to make it coatable. In some cases it may be necessary to dilute the coating solution with additional solvent to provide a more desirable coating viscosity.

The preferred coating device is that disclosed in U.S. Patent Nos. 5,741,549 and 5,759,274. Other coating devices such as a rotogravure coating roll may be used provided that it results in a uniform coating of the hard coat material.

The coated film is passed over roll 33a and then 33c to align it so that coated film 36 may be passed through tunnel oven 37 which preferably is about 120 feet (36.5 meters) in length and has 3 heated zones of 40 feet (12.2 meters) each with zones 1, 2 and 3 being heated respectively at 110° F. (43° C.), 120° F. (49° C.) and 120° F. (49° C.). The coated film may be passed at any convenient speed to assure solvent removal. Preferably, the speed is in the order 55 feet (17 meters) per minute under a film tension of 1 pound per inch (0.18 kg per cm). The film with the dried coating is then passed through curing station 38 which is fitted with a UV source such as high pressure mercury bulbs with a total power output of 67 kilowatts having parabolic reflectors to direct the light to the coated surface of the film producing coated film 42 which exits curing station 38 and is then passed over idler rolls 39a, 39b, 39c, 39d and wound into storage roll 40 for further processing. During drying, forced air is passed through oven 37 in a direction opposite to the direction of film movement.

The hard coated polymeric film on storage roll 40, as depicted in Fig. 4, is then coated with pressure sensitive adhesive to apply a dry coating of pressure sensitive adhesive on the order of 0.1 to 1 mil (0.003 to 0.03 mm), preferably 0.3 mil (0.008 mm) to the surface of coated film 42 opposite that with the hard coat. After the pressure sensitive adhesive layer is applied and dried, a second polymeric film which may be of the same composition as the first polymer film is laminated to the first polymer film by the technique schematically shown in Fig. 4. Film 42 is unwound from roll 40, over idler rolls 44b and 44a past coater station 43 where a solution of the pressure sensitive adhesive is applied in a uniform thickness which will ultimately dry to a thickness preferably of 0.3 mil (0.008 mm), then over idler roll 44c and the adhesive coated film 50 is passed through

tunnel oven 45 which has 4 heated zones with zones 1, 2, 3 and 4 being heated respectively at 80° F. (27° C.), 130° F. (54° C.), 220° F. (104° C.) and 200° F. (93° C.). The slot die for applying the adhesive solution to the film preferably has an opening of about 15 mils (0.38 mm) to provide 0.3 mil (0.008 mm) dry coating. The coated sheet is
5 passed through the oven at a speed of 100 feet per minute under tension of 1 pound per inch (0.18 kg per cm). The dried film 51 exits the tunnel oven and is passed over idler rolls 46a, 46b, 46c to laminator 52 consisting of opposed rolls 47a and 47b where the second polymeric sheet 53 taken from roll 49 is passed over idler roll 48 into the nip between rolls 47a and 47b where the films are laminated together to provide laminated
10 film 54 which is wound onto storage roll 55. Roll 47a is a steel roll which preferably is a 16 inch (40 cm) diameter steel roll which is heated at 160° F. (71° C.) and roll 47b preferably is an 18 inch (46 cm) diameter rubber back-up roll comprised of rubber having a shore A durometer 65. These rolls are forced together under a force of 20 pounds per lineal inch (3.6 kg per lineal cm) during the laminating process.

15 The 2 layer laminate 54 on storage roll 55 is then replaced for roll 49 in the apparatus depicted in Fig. 4. A fresh uncoated roll of polymer film is installed in place of roll 40 of the apparatus depicted in Fig. 4 and it is coated with a 0.3 mil dry coating of pressure sensitive adhesive by coater 43, passed through tunnel over 45 to dry and laminated to laminate 53 at laminator 52, as described above, to provide a 3-film laminate
20 54 which is wound as roll 55 shown in Fig. 4.

The three film laminate 54 on storage roll 55 is then passed again through the same apparatus depicted in Fig. 4 to apply the attachment pressure sensitive adhesive layer and apply a 2 mil (0.5 mm) silicon coated polyester release liner to the freshly coated adhesive layer. In this case the attachment pressure sensitive adhesive layer is extruded from a 15
25 mil (0.38 mm) slot die to obtain a dry coating thickness of 0.8 mil (0.02 mm). The laminating temperature in the case of the attachment of the release liner is 160° F. (71°C.).

Examples

The invention will be more fully understood by reference to the following
30 examples wherein all parts and percentages are by weight unless otherwise indicated.

Adhesive A Solution

(IOA/MA/AA weight ratio 57.5/35/7.5) A mixture of 87.4 grams isooctylacrylate (IOA), 53.2 grams methyl acrylate (MA), 11.4 grams acrylic acid (AA), 248.0 grams ethyl acetate and 0.456 grams 2,2'-azobis(isobutyronitrile) were charged into a one liter bottle.

- 5 The bottle contents were deoxygenated by purging with nitrogen at a flow rate of one liter per minute for two minutes. The bottle was sealed and placed in a rotating water bath at 55°C. for 24 hours to effect essentially complete polymerization. The resulting polymer was diluted with 300 grams of toluene. The inherent viscosity measured in ethyl acetate at a concentration of 0.15 g/dl was 1.80 dl/g.

10

Adhesive B Solution

A mixture of 117.9 grams butyl acrylate, 9.6 grams acrylic acid, 372.5 grams acetone and 0.19 gram 2,2'-azobis (2-methylbutane nitrile) were charged with a one liter bottle. The bottle contents were deoxygenated by purging with nitrogen at a rate of one
15 liter per minute for 2 minutes. The bottle was sealed and placed in a rotating water bath at 57°C. for 24 hours to effect essentially complete polymerization. A 0.15 g/dl concentration solution of the resulting polymer had a measured inherent viscosity of 1.05 dl/g.

20

<u>Adhesive C Solution</u>	<u>Percent by Weight</u>
Adhesive A Solution	40.47
Adhesive B Solution	33.11
Ethyl acetate	25.75
Ultra violet light absorber ¹	0.37
25 Cross linker solution ²	0.29

30

Adhesive C Solution was prepared under ambient conditions by combining the above ingredients in a 55 gallon drum (208 liter) and mixing for 30 minutes with a 12 inch (30.5 cm) propeller type mixing blade at 500 rpm. The solution was left undisturbed to eliminate bubbles and then used for coating.

¹ Bis (2,4 dihydroxy phenyl)-methanone available under the tradename UVINUL™ 3050 from BASF, Charlotte, NC.

Adhesive C Solution had an initial viscosity of 960 cps when measured at room temperature with a Brookfield viscometer using a No. 3 spindle at 30 rpm.

	<u>Adhesive D Solution</u>	<u>Percent by Weight</u>
5	Adhesive A Solution	73.58
	Ethyl acetate	25.75
	Ultra violet light absorber ¹	0.37
	Cross linker solution ²	0.29

10 Adhesive D Solution was prepared under ambient conditions by combining the above ingredients in a 55 gallon (208 liter) drum and mixing for 30 minutes with a 12 inch (30 cm) propeller type mixing blade at 500 rpm. The solution was left undisturbed to eliminate bubbles and then used for coating.

15 Adhesive D Solution had an initial viscosity of 2700 cps when measured at room temperature with a Brookfield viscometer using a No. 3 spindle at 30 rpm.

Adhesive E Solution

Adhesive E Solution was a co-polyester solution commercially available under the trade designation Bostik Vitel™ 3300 from Bostik Inc. of Middleton, MA, which was
20 diluted to 15% solids with 80/20 by volume mixture of toluene/methyl ethyl ketone.

Hardcoat Coating Composition

Identification of Ingredients

Nalco 2327 is an aqueous dispersion (40% solids) of colloidal silica particles
25 having an average particle diameter of 20 nanometers, available from Nalco Chemicals Co., Chicago, IL.

Z6030 is 3-(trimethoxysilyl) propyl methacrylate available from Dow Corning Co.,
Midland, MI.

PETA is pentaerythritol acrylate, available from Aldrich Chemicals Co.,
30 Milwaukee, WI.

² 5% by weight solution of 1,1'-isophthaloyl bis (2-methylaziridine) in toluene.

NNDMA is N,N-dimethyl acrylamide, available from Aldrich Chemical Co., Milwaukee, WI.

The following ingredients were charged into a 10 liter round-bottomed flask:

	<u>Ingredient</u>	<u>Weight (g.)</u>
5	Nalco 2327	1195
	NNDMA	118
	Z6030	120
	PETA	761

The flask was then placed on a rotary evaporator (Bucchi™ R152 available from Bucchi Laboratory AG, Flanil, Switzerland) in a bath heated at 55° C. A refrigerated mixture 50:50 by volume water: ethylene glycol antifreeze was recirculated through the evaporator cooling coils. The volatile components were removed at a reduced pressure of about 25 Torr. until the distillation rate was reduced to less than 5 drops per minute (approximately 2 hours). The resulting material (1464g.) was a clear liquid, containing less than 1% water (as determined by Carl Fisher Titration) which comprised 54.2 wt% PETA, 8.4 wt% NNDMA and 38.8 wt% acrylated silica. This material was dissolved in isopropyl alcohol to make a 50% solids solution, hereafter referred to as ("Hardcoat Coating Composition").

Example 1

The Hardcoat Coating Composition described above was further diluted with isopropyl alcohol to obtain a 21% solids solution to which was added 0.1% by weight of a smoothing agent (Dow™ 57). The resultant coating composition was coated by use of equipment shown in Fig. 3, with an extrusion die. The coating was applied to a polyester film (Melinex™ 454-200) to obtain, after drying and curing, a dry coating weight of 0.3 gram per square foot (3.2 grams per square meter).

The coating conditions for the equipment shown in Fig. 3 were as follows:

Extrusion die³ opening: 4 mil (0.38 mm)

Film speed: 55 feet per minute (16.8 meters per minute)

Film tension: 1 lb/inch (0.18 kg per cm)

Oven zone temperatures: (1): 110° F. (43° C.); (2): 120° F. (49° C.);
(3): 120° F. (49° C.)

³ Disclosed in U.S. Patent Nos. 5,741,549 and 5,759,274.

Oven zone length: 40 feet (12.2 meters)

Coating width: 52 inches (1.32 meter)

UV light source: high pressure mercury bulb with parabolic reflectors –
67 kw total output

5 Two uncoated Melinex™ 454-200 films were laminated together by use of the equipment depicted in Fig. 4. The first of the films was coated with Adhesive C Solution described above using an extrusion die having an opening of 15 mils (0.38 mm) to provide a dry adhesive coating of 0.3 mil (0.008 mm). The film speed was 100 feet (30.5 meters) per minute under a tension of about 1 lb per inch (0.18 kg per cm). The oven had four 40
10 foot (12.2 meter) heated zones, heated as follows: (1) 80° F. (27° C.); (2) 130° F. (54° C.); (3) 220° F. (104° C.) and (4) 200° F. (93° C.). The second film was laminated to the adhesive coated side of the first film at nip rolls 47a and 47b depicted in Fig. 4. Nip roll 47a was a 16 inch (41 cm) diameter steel roll heated at 160° F. (71° C.) and roll 47b was an 18 inch (46 cm) diameter rubber roll having a Shore A durometer of 65. The rolls were
15 forced together under a force of 20 pounds per lineal inch (3.6 kg per lineal cm).

The 2-film laminate was then laminated to the surface opposite of the hardcoated film described above by use of the equipment depicted in Fig. 4. The 2-film laminate was first coated with Adhesive C solution, as described above, by use of the extrusion die with a 15 mil (0.38 cm) opening to provide a 0.3 mil (0.008) dry adhesive coating.

20 The 3-film laminate was then coated on the surface opposite the hard coating with a 0.8 mil (0.02 mm) dry thickness obtained from Adhesive C Solution described above by use of the extrusion die with a 15 mil (0.38 mm) opening. The drying conditions were the same as described above except the film speed was 50 feet (15.25 meter) per minute. A 2 mil (0.05 mm) silicone coated polyester release liner was applied to surface of the
25 adhesive. The release liner was commercially available from CP Films Corp. of Martinsville Virginia under the trade designation Clearsil™ T10. The resultant laminate was then wound onto a roll and slit to commercial size.

The film produced as described above was laminated to various types of glass using a 48 inch (1.22 meter) hand powered two-roll laminator. Each roller is 4 inches (10
30 cm) in diameter and covered with 3/16 inch (0.48 cm) of rubber (Shore A 70 durometer). The force applied during lamination of the film to the glass was approximately 20 pounds per linear inch (3.6 kg per lineal cm).

Example 2

Example 2, which is a comparative example, was prepared in the same manner as Example 1, with the exception being that the pressure sensitive adhesive was obtained
5 from Adhesive D Solution to show the effect of using a stiffer pressure sensitive adhesive.

Example 3

Example 3 was made according to the present invention. One uncoated Melinex™
454-400 4 mil thick film (0.1 mm) and one uncoated Melinex™ 454-300 3 mil film
10 (0.076 mm) were laminated together by use of the equipment depicted in Fig. 4. The first
of the films was coated with Adhesive C Solution described above using a notch bar coater
having a coating gap between the bar and the film of 4 mils (0.102 mm) to provide a dry
adhesive coating of 0.45 mil (0.011 mm). The film speed was 10 feet (3.05 meters) per
minute under a tension of about 1 lb per inch (0.18 kg per cm). The oven had three 12
15 foot (3.7 meter) heated zones, heated as follows: (1) 120° F. (49° C.); (2) 180° F. (82° C.);
and (3) 200° F. (93° C.). The second film was laminated to the adhesive coated side of the
first film at nip rolls 47a and 47b depicted in Fig. 4. Nip roll 47a was a 16 inch (41 cm)
diameter steel roll heated at 160° F. and roll 47b was an 18 inch (46 cm) diameter rubber
roll having a Shore A durometer of 65. The rolls were forced together under a force of 20
20 pounds per lineal inch (3.6 kg per lineal cm).

The 2-film laminate was then coated with a 1.0 mil (0.0254 mm) dry thickness of
adhesive obtained from Adhesive C Solution described above by use of the notch bar
coater with a 7 mil (0.178 mm) gap between the bar and the uncoated film. The drying
conditions were the same as described above. A 2 mil (0.051 mm) silicone coated
25 polyester release liner was applied to the dried surface of the adhesive. The release liner
was commercially available from CP Films Corp. of Martinsville Virginia under the trade
designation Clearsil™ T10. The resultant laminate was then wound onto a roll.

Example 4

30 Example 4 is a comparative example which only includes a single layer of 7 mil
(0.178 mm) polyester film to show the need for at least two film layers as required by the
present invention. One uncoated Melinex™ 454-700 film was coated with Adhesive C

Solution described above using a notch bar coater having a coating gap between the bar and the film of 7 mils (0.178 mm) to provide a dry adhesive coating of 0.8 mil (0.02 mm). The film speed was 10 feet (3.04 meters) per minute under a tension of about 1 lb per inch (0.18 kg per cm). The oven had three 12 foot (3.7 meter) heated zones, heated as follows:

5 (1) 120° F. (49° C.); (2) 180° F. (82 C.); and (3) 200° F. (93° C.).

A 2 mil (0.05 mm) silicone coated polyester release liner was applied to surface of the adhesive. The release liner was commercially available from CP Films Corp. of Martinsville Virginia under the trade designation Clearsil™ T10. The resultant laminate was then wound onto a roll.

10

Example 5

Example 5 is also a comparative example which, like Example 3, uses a 4 mil (0.1 mm) and a 3 mil (0.076 mm) polymer films, but with a stiffer pressure sensitive adhesive to show that the selection of the pressure sensitive adhesive is important to provide a

15 laminate which will perform in an acceptable manner. One uncoated Melinex™ 454-400 and one uncoated Melinex TM 454-300 films were laminated together by use of the equipment depicted in Fig. 4. The first of the films was coated with Adhesive E Solution described above using a notch bar coater having a coating gap between the bar and the

20 film of 3 mils (0.076 mm) to provide a dry adhesive coating of 0.2 mil (0.0051 mm). The film speed was 10 feet (3 meters) per minute under a tension of about 1 lb per inch (0.18 kg per cm). The oven had three 12 foot (3.7 meter) heated zones, heated as follows: (1) 120° F. (49° C.); (2) 180° F. (82.2° C.); and (3) 200° F. (93° C.). The second film was laminated to the adhesive coated side of the first film at nip rolls 47a and 47b depicted in Fig. 4. Nip roll 47a was a 16 inch (41 cm) diameter steel roll heated at 160° F. and roll

25 47b was an 18 inch (46 cm) diameter rubber roll having a Shore A durometer of 65. The rolls were forced together under a force of 20 pounds per lineal inch (3.6 kg per lineal cm).

The 2-film laminate was then coated with a 0.8 mil (0.02 mm) dry thickness of Adhesive D Solution described above by use of the notch bar coater with a 7 mil (0.178 mm) gap between the bar and the uncoated film. The drying conditions were the same as

30 described above. A 2 mil (0.05 mm) silicone coated polyester release liner was applied to surface of the adhesive. The release liner was commercially available from CP Films

Corp. of Martinsville Virginia under the trade designation Clearsil™ T10. The resultant laminate was then wound onto a roll.

The composition of each of Examples 1-5 is set forth in Table 1.

5

Table 1

Ex. No.	Adhesive Solution	Adhesive Modulus at 22°C (MPa)	Layers of Film	Film Thickness (mils)	Film Thickness (mm)
1	C	0.33	3	2, 2, 2	0.05, 0.05, 0.05
2	D	0.51	3	2, 2, 2	0.05, 0.05, 0.05
3	C	0.33	2	4, 3	0.1, 0.076
4	C	0.33	1	7	0.178
5	D/E	0.51/65	2	4, 3	0.1, 0.076

The tests performed on Examples 1-5 are as follows:

10 **Boiling Water Test**

The film was applied to a 4 inch by 9 inch (10.2 cm by 22.9 cm) clear glass plate then immersed in boiling water for 2 hours. After two hours the sample was removed and examined. The film was examined to see if it was still attached to the glass, bubbles developed in the adhesive layers or otherwise was altered by the boiling water. Passing this test requires that the unaltered sample still remain attached to the glass.

15

Impact Test

The film laminate was laminated to a number of 12 inch by 12 inch (30.5 cm by 30.5 cm) test glass plates, both laminated and tempered. The laminating device was a simple roller, approximately 20 pounds per linear inch (3.6 kg per lineal cm) force was used to adhere the film to the glass. Impact testing was conducted on 12 inch by 12 inch (30.5 by 30.5 cm) pieces of 0.17 inch (4.3 mm) thick laminated glass with a 30 mil (0.76 mm thick internal polyvinylbutyral interlayer) and on 12 inch by 12 inch (30.5 by 30.5 cm) 1/8 inch thick (3.18 mm) tempered glass. The test glass plate was held horizontally in a frame with the film laminate adhered beneath the glass plate while a 0.5 pound (0.23 kg) steel ball was dropped from 30 feet (9.14 m) onto the center of the glass plate to fracture the glass plate. The fractured assembly was then examined to see if there was tearing or

20

25

ripping of the film laminate. Passing this test requires that, on at least one type of glass substrate, i.e., either laminated or tempered, the laminate is neither penetrated nor torn.

Light Transmission and Haze Testing

The film laminate was laminated to a 4 inch by 4 inch (10.2 cm by 10.2 cm) piece of 0.125 inch (3.2 mm) clear glass using a simple roller and 20 pounds per linear inch (3.6 kg per lineal cm) of force. After lamination, the specimen was tested using a Pacific Scientific™ Colorimeter model number XL-835. The device was programmed to measure visible light transmission, yellow index and haze (Function 10). Four measurements were taken from different areas of the sample, with the results being shown in Table 2.

The sample was then abraded in a Taber™ Abrader with CS-10F as the abrasive material under a 500 gram load. Results after 1000 revolutions on the Taber™ Abrader are also reported in Table 2.

The test results of testing Examples 1-5 are shown in Tables 2-4.

Table 2

Example No.	Boiling Water Test	Transmission Before Abrader		Transmission After Abrader	
		Transmission (%)	Haze (%)	Transmission (%)	Haze (%)
1	Passed ^{4,5}	90.4	1.75	90.0	7.2
2	Passed ^{4,5}	89.2	1.02	89.3	7.2
3	Passed ^{4,5}	88.6	2.0	N.A. ⁷	N.A. ⁷
4	Passed ^{4,5}	89.8	1.53	N.A. ⁷	N.A. ⁷
5	Failed ^{4,6}	89	1.0	N.A. ⁷	N.A. ⁷

⁴ A slight haze had developed in the film but this disappeared within 24 hours.

⁵ No adhesive failure or bubbles in adhesive.

⁶ Small bubbles formed in the adhesive which remained after testing.

⁷ Not applicable since the laminate did not include a hardcoat.

Table 3

Impact Testing Results – Laminated Glass		
Example No.	Penetration	Film Failure
1	no ⁸	no ⁸
2	no ⁹	no ⁹
3	no ⁸	no ⁸
4	no ⁸	yes ¹¹
5	no ⁸	yes ⁸

Table 4

Impact Testing Results – Tempered Glass		
Example No.	Penetration	Film Failure
1	yes ¹²	yes ¹³
2	no ⁹	yes ¹⁰
3	no ⁸	no ⁸
4	yes ⁸	yes ⁸
5	yes ¹¹	yes ¹²

⁸ Same result in five tests.⁹ Same result in four tests.¹⁰ Failed in 3 of 4 tests.¹¹ Failed in 1 of 5 tests.¹² Failed in 2 of 5 tests.¹³ Failed in 3 of 5 tests.

What is claimed is:

1. An optically clear laminate suited for attachment to window glass to provide a glazing element which has reduced spall and lacerative consequences on impact fracture of the window glass; said laminate comprising:
 - (a) a first lamina comprised of optically clear flexible nonadhesive polymeric material having a first major surface and an opposite second major surface;
 - (b) a scratch-resistant hard coating over said first major surface to provide an exposed surface to the laminate;
 - (c) at least one additional lamina comprised of optically clear flexible nonadhesive polymeric material;
 - (d) a sufficient number of layers of in situ optically clear pressure sensitive adhesive layers to directly bond said laminae together with the hard coating exposed; and
 - (e) a layer of in situ optically clear ambient temperature attachable pressure sensitive adhesive to bond said laminate to window glass.
2. The laminate of claim 1 wherein each of said laminae has a thickness no greater than about 5 mils (0.13 mm).
3. The laminate of claim 1 wherein each of said laminae is comprised of biaxially oriented polyester film.
4. The laminate of claim 1 wherein said pressure sensitive adhesive is comprised of acrylic based copolymer.
5. The laminate of claim 1 further including a third lamina comprised of optically clear flexible polymeric material.
6. The laminate of claim 1 wherein the hard coating comprises a cured ceramer.

7. The laminate of claim 1 wherein once attached to tempered or laminated window glass provides a glazing element which passes at least one of the following ANSI Z-26 tests:

- 5.04 – Two Hour Boiling Water;
- 5.13 – Thirty Foot Ball (9.14 m) Drop;
- 5.17 – Resistance to Abrasion;
- 5.19 – Chemical Resistance; and
- 5.23 – Flammability.

10 8. The laminate of claim 1 wherein said pressure sensitive adhesive layers are comprised of pressure sensitive adhesive having a shear storage modulus measured at 22°C in the range of about 0.20 MPa to about 0.50 MPa.

15 9. An optically clear glazing element which has reduced spall and lacerative consequences on impact fracture, said glazing element comprising:





- (a) a first lamina comprised of optically clear flexible polymeric material having a first major surface and an opposite second major surface;
- (b) a scratch-resistant hard coating over said first major surface;
- (c) at least one additional lamina comprised of optically clear flexible nonadhesive polymeric material;
- (d) a sufficient number of layers of in situ optically clear pressure sensitive adhesive layers to directly bond said laminae together with the hard coating exposed;
- (e) a layer of in situ optically clear ambient temperature attachable pressure sensitive adhesive to bond said laminate to window glass; and
- 25 (f) tempered or laminated window glass.

10. The glazing element of claim 9 wherein said window glass is tempered.

30 11. The glazing element of claim 9 wherein said pressure sensitive adhesive layers are comprised of pressure sensitive adhesive having a shear storage modulus measured at 22°C in the range of about 0.20 MPa to about 0.50 MPa.

12. An optically clear laminate comprising the following components adhered together in the following order:

- (a) a scratch-resistant hard coat comprised of cured ceramer;
 - (b) a first biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm);
 - (c) a first pressure sensitive adhesive layer;
 - (d) a second biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm);
 - (e) a second pressure sensitive adhesive layer;
 - (f) a third biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm); and
 - (g) a third ambient-temperature-attachable pressure sensitive adhesive layer;
- wherein said pressure sensitive adhesive layers are comprised of pressure sensitive adhesive having a shear storage modulus measured at 22°C in the range of about 0.20 MPa to 0.50 MPa.

**Fig. 1****Fig. 2****Fig. 3****Fig. 4**

INTERNATIONAL SEARCH REPORT

Internat application No

PCT/US 01/13609

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B32B27/36 B32B17/10 C03C17/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C B32B C08J C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 893 248 A (MITSUBISHI POLYESTER FILM CORP) 27 January 1999 (1999-01-27) claims 1,4 page 1, line 5 - line 7 page 4, line 26 - line 45 example 1	1-6,9, 10,12
X	WO 99 30905 A (FURUYA KOJI ;KAWAI SHINICHI (JP); SUZUKI KENJI (JP); TEIJIN LTD (J) 24 June 1999 (1999-06-24) abstract	1-3,6,9
P,X	& EP 1 040 914 A (TEIJIN LIMITED) 4 October 2000 (2000-10-04) claims 1,10,13 page 6, line 46 - line 58	1-3,6,9
	--- -/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

7 November 2001

Date of mailing of the international search report

15/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hillebrand, G

INTERNATIONAL SEARCH REPORT

 Internati Application No
 PCT/US 01/13609

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 319 911 A (NIPPON SHEET GLASS CO LTD) 14 June 1989 (1989-06-14) claims 1,15,16 page 5, line 21 - line 25 ---	1-3,6
X	US 4 634 637 A (OLIVER DELL B ET AL) 6 January 1987 (1987-01-06) claims 1,2,4-6 column 6, line 20 - line 29 ---	1,4,9
X	US 4 898 786 A (SWOFFORD HOWARD W) 6 February 1990 (1990-02-06) claims 1,3 column 6, line 8 - line 36 ---	1-3,9
X	US 4 242 403 A (BARTUS STEPHEN P JR ET AL) 30 December 1980 (1980-12-30) claim 1 ---	1,9
X	EP 0 353 677 A (LINTEC CORP) 7 February 1990 (1990-02-07) claims 1,2,6 page 7, line 35 - line 40 example 1 ---	1
A	WO 94 13467 A (HOECHST AG ;HOECHST CELANESE CORP (US); BENNETT CYNTHIA (DE); CHOE) 23 June 1994 (1994-06-23) claims 1,12,13 page 14, line 17 - line 30 ---	1
A	EP 0 317 858 A (HOECHST CELANESE CORP) 31 May 1989 (1989-05-31) claims 1,6,7,10,11 page 2, line 14 - line 54 ---	1
A	US 4 211 823 A (SUZUKI MASAHARU ET AL) 8 July 1980 (1980-07-08) claims 1,11 ---	1
A	EP 0 527 080 A (CHEIL SYNTHETICS INC) 10 February 1993 (1993-02-10) claim 1 ---	1
A	US 4 945 002 A (TANUMA ITSUO ET AL) 31 July 1990 (1990-07-31) cited in the application claims 1,3,4 ---	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/13609

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0893248	A	27-01-1999	EP 0893248 A1	27-01-1999
			US 6242081 B1	05-06-2001
			WO 9826929 A1	25-06-1998
			JP 10230577 A	02-09-1998
WO 9930905	A	24-06-1999	EP 1040914 A1	04-10-2000
			WO 9930905 A1	24-06-1999
EP 0319911	A	14-06-1989	DE 3888940 D1	11-05-1994
			EP 0319911 A2	14-06-1989
			JP 1253444 A	09-10-1989
			US 4925737 A	15-05-1990
US 4634637	A	06-01-1987	NONE	
US 4898786	A	06-02-1990	AU 605738 B2	17-01-1991
			AU 3593089 A	21-12-1989
			BR 8902879 A	01-02-1990
			CA 1328585 A1	19-04-1994
			CN 1038658 A	10-01-1990
			DE 68924100 D1	12-10-1995
			DE 68924100 T2	09-05-1996
			DE 346768 T1	05-07-1990
			DK 290789 A	16-12-1989
			EP 0346768 A2	20-12-1989
			FI 892945 A	16-12-1989
			IE 191689 L	15-12-1989
			JP 2038432 A	07-02-1990
			JP 6025273 B	06-04-1994
			KR 9310655 B1	05-11-1993
			MX 169509 B	08-07-1993
			NO 892475 A	18-12-1989
			US 5064722 A	12-11-1991
			US 5082738 A	21-01-1992
			ZA 8904480 A	28-02-1990
US 4242403	A	30-12-1980	AR 215014 A1	31-08-1979
			AU 509669 B2	22-05-1980
			AU 2743777 A	01-02-1979
			BE 857315 A1	14-11-1977
			BR 7705035 A	30-05-1978
			CA 1111725 A1	03-11-1981
			DE 2735175 A1	09-02-1978
			ES 461238 A1	01-05-1978
			FI 772283 A ,B,	03-02-1978
			FR 2360526 A1	03-03-1978
			GB 1580353 A	03-12-1980
			IT 1080072 B	16-05-1985
			JP 53019314 A	22-02-1978
			JP 60039546 B	06-09-1985
			LU 77881 A1	28-10-1977
			MX 4572 E	17-06-1982
			NL 7708474 A	06-02-1978
			NZ 184797 A	05-03-1980
			SE 433723 B	12-06-1984
			SE 7708756 A	03-02-1978
			ZA 7704487 A	28-06-1978

INTERNATIONAL SEARCH REPORT

In relation on patent family members

International Application No

PCT/US 01/13609

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0353677	A	07-02-1990	JP 2043045 A	13-02-1990
			JP 2065999 C	24-06-1996
			JP 7091515 B	04-10-1995
			JP 2058584 A	27-02-1990
			JP 2066000 C	24-06-1996
			JP 7091517 B	04-10-1995
			AU 620427 B2	20-02-1992
			AU 3927589 A	08-02-1990
			DE 68922037 D1	11-05-1995
			DE 68922037 T2	28-09-1995
			EP 0353677 A2	07-02-1990
WO 9413467	A	23-06-1994	KR 9108849 B1	21-10-1991
			WO 9413467 A1	23-06-1994
			EP 0673309 A1	27-09-1995
EP 0317858	A	31-05-1989	JP 8504383 T	14-05-1996
			US 4822828 A	18-04-1989
			CA 1314647 A1	16-03-1993
			DE 3871730 D1	09-07-1992
			DE 3871730 T2	21-01-1993
			DE 317858 T1	16-11-1989
			DK 650788 A	24-05-1989
			EP 0317858 A2	31-05-1989
			JP 7068705 A	14-03-1995
			JP 1188509 A	27-07-1989
			KR 9301353 B1	27-02-1993
US 4211823	A	08-07-1980	NO 885203 A	24-05-1989
			SE 8804218 A	22-11-1988
			JP 1112154 C	16-09-1982
			JP 53111336 A	28-09-1978
			JP 57002735 B	18-01-1982
			AU 520716 B2	25-02-1982
			AU 3397678 A	13-09-1979
			BE 864691 A1	11-09-1978
			BR 7801476 A	28-11-1978
			CA 1118929 A1	23-02-1982
			CH 628366 A5	26-02-1982
EP 0527080	A	10-02-1993	DE 2810072 A1	21-09-1978
			FR 2383220 A1	06-10-1978
			GB 1596107 A	19-08-1981
			IT 1109127 B	16-12-1985
			NL 7802636 A ,B,	13-09-1978
			SE 444444 B	14-04-1986
			SE 7802753 A	12-09-1978
			DE 69227287 D1	19-11-1998
			DE 69227287 T2	06-05-1999
			EP 0527080 A1	10-02-1993
			JP 5245922 A	24-09-1993
US 4945002	A	31-07-1990	KR 9403889 B1	04-05-1994
			US 5302459 A	12-04-1994
			JP 2521058 B2	31-07-1996
			JP 63056444 A	11-03-1988
			JP 63082813 A	13-04-1988
			CA 1314801 A1	23-03-1993

INTERNATIONAL SEARCH REPORT

In relation to patent family members

International application No

PCT/US 01/13609

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4945002	A	DE 3786504 D1	19-08-1993
		DE 3786504 T2	02-12-1993
		EP 0258063 A2	02-03-1988
		US 5085721 A	04-02-1992
<hr/>			

THIS PAGE BLANK (USPTO)